

Trade name: SE-36

TDS

Wudi De Xin Chemical Co. Ltd.

Address: High-tech Zone Wudi County, Shandong, China
Tel: 86-543-6452566

P.C. 251909
Fax: 86-543-6452566

Description

SE-36 polyol is a glycerine propoxylated polyether triol with an average molecular weight of 5000 and EO-cap and high EO content, BHT and amine free and high active. It is mainly used for LR foam, molded foam and other.

Characteristic data

| Typical Properties | Units | Limits | Test Methods |
|-----------------------------|------------|-----------------|--------------------|
| Hydroxyl value | mg KOH/g | 33-36 | GB/T 12008.3-2009 |
| Water, max. | % | 0.05 | GB/T 22313-2008 |
| Acid number, max. | mgKOH/g | 0.08 | GB/T 12008.5-2010 |
| Colour, max | APHA | 50 | GB/T 605-2006 |
| potassium,max | mg/kg | ≤5 | GB/T 12008.4-2009 |
| Viscosity | mpa.s(25℃) | 1200~1600 | GB/T 12008.7-2010 |
| pH | | 5~8 | GB/T 12008.2-2010 |
| Appearance / physical state | | liquid, viscous | Q/SH 1065 002-2010 |

Package:

200KG in iron drum

Precaution:

Keep containers tightly closed so as to protect them from rays of light and moisture.
